

TECHNICAL DATA SHEET



Key Highlights

- Fibre glass reinforced layer
- **GROUP - T** 'Wear Resistance'

SPECIFICATION ACCORDING TO EN 649

CHARACTERISTICS	STANDARD	UNIT	RESULT
STRUCTURE			
Type of flooring	EN649	n/a	Heterogeneous Sheet
Material	n/a	n/a	Polyvinylchloride
Coating	n/a	n/a	PUR Coating for easy maintenance
Pattern	n/a	n/a	Wood
SAFETY CRITERIA			
Flammability	GB 8624-2006	class	B _{fl} -s1
Slip resistance	DIN 51130	group	R9
PERFORMANCE BEHAVIOR			
Sheet width	EN 426	m	2
Sheet length	EN 426	m	≥ 20
Overall thickness	EN 426	mm	1.6
Wear layer thickness	EN429	mm	0.2
Dimensional stability	EN 434	n/a	X : <0.4%
Residual indentation	EN 433	mm	0.1
Wear resistance	EN 649	group	T
Color fastness	ISO 105-B02	rating	≥ 6
ADDITIONAL PROPERTY			
Castor chair ✓	Underfloor heating ✓	Antimicrobial and antifungal ✓	
Antistatic behavior ✓	Chemical resistance ✓		