



HPVA Laboratories
42777 Trade West Drive, Sterling, VA 20166
PHONE 703-435-2900 FAX 703-435-2537

Report On
Smoke Density Characteristics
As Determined By
ASTM E 662 Test Method

PREPARED FOR:
Armstrong Flooring Inc.
Lancaster, PA

TEST NUMBER: S-2204

Rejuvenations

Date of Issue:
1/29/2018





I. INTRODUCTION

The following Scope, Summary of Test Method, Test Specimens, and Specimen Conditioning sections are abridged from the Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials ASTM E662-17A.

II. SCOPE

This fire-test response standard covers determination of the specific optical density of smoke generated by solid materials and assemblies mounted in the vertical position in thicknesses up to and including one inch. The test is based on the attenuation of a light beam by smoke accumulating within a closed chamber due to nonflaming pyrolytic decomposition and flaming combustion. Results are expressed in terms of specific optical density which is derived from a geometrical factor and the measured optical density, a measurement characteristic of the concentration of smoke.

The test is intended for use in research and development and not as a basis for ratings for regulatory purposes. At the present time, no means are provided for predicting the density of smoke which may be generated by the materials exposed to heat and flame under other fire conditions.

III. SUMMARY OF TEST METHOD

This method employs an electrically-heated radiant energy source mounted within an insulated ceramic tube and positioned so as to produce an irradiance level of 2.2 BTU/ft² sec. (2.5W/cm²) averaged over the central 1.5 inch diameter area of a vertically mounted specimen facing the radiant heater. The nominal 3 by 3 inch specimen is mounted within a holder which exposes an area measuring 2 9/16 by 2 9/16 inch. The holder can accommodate specimens up to one inch thick. This exposure provides the nonflaming condition of the test.

For the flaming condition, a six-tube burner is used to apply a row of air-propane flamelets across the lower edge of the exposed specimen area and into the specimen holder trough. The application of flame in addition to the specified irradiance level from the heating element constitutes the flaming combustion exposure.

The test specimens are exposed to the flaming and nonflaming conditions within a closed 18 ft³ chamber. A photometric system with a 36 inch vertical light path measures the decrease in light transmission as smoke accumulates.

IV. TEST SPECIMENS

The test specimens are 3 by 3 +/- .03 inch by the intended installation thickness up to and including 1 inch thickness. Materials in thicknesses in excess of 1 inch are sliced to 1 inch and the original (uncut) surface tested. Multi-layer materials thicker than 1 inch with surface facings of different materials are sliced to 1 inch thickness, and each original (uncut) surface tested separately, if both surface facings are exposed to fire.

V. SPECIMEN CONDITIONING

Specimens are predried for 24 hours at 140 ± 5°F (60 ± 3°C) and then conditioned to equilibrium (constant weight) at an ambient temperature of 73 ± 5°F (23 ± 3°C) and a relative humidity of 50 ± 5 percent.



**Report on Smoke Density Characteristics as Determined by:
 ASTM E 662 Test Method**

Test Number: S-2204	Test Date: 01/24/18
----------------------------	----------------------------

Report Prepared For:	Armstrong Flooring Inc. Lancaster, PA
Material Tested:	Rejuvenations

Sample Information:

Detailed Product Description:	Rejuvenations - Heterogeneous Sheet Flooring. Vinyl Sheet with a 0.55mm wear layer, Width: 2000mm, Gauge: 2.0mm. Production Date: 12/04/17, Lot Number: 1712045151. Comparable Products: RejuvenationsClassics, ColorWin, DecorArt, Timberline, Translations, Perspectives.		
Sample Preparation:	The material was adhered to a 1/4" cement board backer by the manufacturer using Armstrong S240 adhesive.		
Sample Selection By:	Manufacturer	Sample Color:	Brown
Number of Specimens:	6	Conditioning Days:	12

Test Conditions:

Radiometer Reading (mV):	7.19	Irradiance (W/cm2):	2.5
Furnace Temp. (°F):	1315	Specimen Holder Used:	Trough

Test Data (Non- Flaming Exposure Mode):

	Burn 1	Burn 2	Burn 3	Average
Thickness (in.):	0.332	0.330	0.334	0.332
Weight (g):	63.07	63.35	62.70	63.04
Chamber Pressure:	3.4	3.4	3.4	3.4
Chamber Temp. (°F):	94	94	95	94
Smoke Color:	Grey	Grey	Grey	Grey
90 Second Ds:	6	14	6	<u>9</u>
4 Minute Ds:	173	159	171	<u>168</u>
Max Dm:	482	447	481	470
Time to Max Dm (minutes):	16.40	15.15	15.28	15.61
Corrected Dm:	470	441	477	<u>463</u>

Test Data (Flaming Exposure Mode):

	Burn 1	Burn 2	Burn 3	Average
Thickness (in.):	0.332	0.332	0.326	0.330
Weight (g):	63.46	62.75	62.62	62.94
Chamber Pressure:	3.4	3.4	3.4	3.4
Chamber Temp. (°F):	94	95	97	95
Smoke Color:	Grey	Grey	Grey	Grey
90 Second Ds:	69	100	93	<u>87</u>
4 Minute Ds:	209	238	206	<u>218</u>
Max Dm:	353	385	291	343
Time to Max Dm (minutes):	13.48	13.45	14.70	13.88
Corrected Dm:	340	371	275	<u>329</u>

Observations:	All Burns: The material expanded toward the furnace.	
Remarks:	Reported weights and thicknesses include the cement board backer.	
Test Operator	CP	Note: Ds = Specific Optical Density; Dm = Max Specific Optical Density

Report Prepared By:

Manager of Fire Testing – Engineer

Report Reviewed By:

Director – HPVA Laboratories

This is a factual report of the results obtained from laboratory tests of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The HPVA does not verify the description of the materials and products when the description is provided by the client. This report is not a recommendation or a disapprobation by the HPVA of the material or product tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.