



The test report attached verifies the fire performance for Armstrong Sheet Flooring. The product tested is representative of, but may not be identical to the product you are purchasing. Changes in product formulation that occur for a variety of reasons may cause fluctuations in results. The above referenced data is representative of the current formulation of these products. Specifications and interpretation of fire test methods are subject to ongoing development. To assure that the information continues to be current, it is suggested that you request product certification for a specific project. The certification will reference the current applicable independent laboratory test reports.

Report On
Critical Radiant Flux of Floor-Covering Systems
Using a Radiant Heat Energy Source
As Determined By
ASTM E 648 Test Method

PREPARED FOR:
Armstrong World Industries, Inc. Innovation Center
Lancaster, PA
TEST NUMBER: FRP-904

Armstrong Inlaid Commercial Sheet Flooring: POSSIBILITIES Petit
Point

Date of Issue:
2/12/2014





I. SCOPE

This report contains the reference to the test method, purpose, test procedure, preparation and conditioning of test samples, description of materials, test and post test observation data, and test results.

II. TEST METHOD

The test was conducted in accordance with ASTM Designation E 648, "Standard Method of Test for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source." The test is also described by NFPA No. 253.

III. PURPOSE

The purpose of the test is to determine the critical radiant flux of horizontally-mounted floor covering systems exposed to a flaming ignition source in a graded radiant heat energy environment maintained in a test chamber. The specimen may be mounted over underlayment, a simulated concrete structural floor, bonded to a simulated structural floor, or otherwise mounted in a typical and representative way.

The test method provides a basis for estimating one aspect of fire exposure behavior for floor covering systems. The imposed radiant flux is designed to simulate the thermal radiation levels likely to impinge on the floors of a building whose upper surfaces are heated by flames and/or hot gases from fully developed fire in an adjacent room or compartment. The method was developed to simulate an important fire exposure component of fires which may develop in corridors or exit ways of buildings and is not intended for routine use in estimating flame spread behavior of floor covering in building areas other than corridors or exit ways.

IV. TEST PROCEDURE

The basic elements of the test chamber are: 1) an air-gas, fueled radiant heat energy panel inclined at 30° to and directed at 2) a horizontally-mounted floor covering system specimen. The radiant panel generates a radiant energy flux distribution ranging along the 100-cm length of the test specimen from a nominal maximum of 1.0 watts/cm² to a minimum of 0.1 watts/cm². The test is initiated by open flame ignition from a pilot burner. The distance burned to flame-out is converted to watts/cm² and reported as **critical radiant flux**.



Report on Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source as Determined by the ASTM E 648 Flooring Radiant Panel

Test Number: FRP-904

Test Date: 01/23/14

Report Prepared For:	Armstrong World Industries, Inc. Innovation Center Lancaster, PA
Material Tested:	Armstrong Inlaid Commercial Sheet Flooring: POSSIBILITIES Petit Point

Sample Information:			
Detailed Product Description: Armstrong Inlaid Commercial Sheet Flooring: POSSIBILITIES Petit Point			
Sample Preparation: Adhered to 1/4" cement board with Armstrong S-599 Adhesive by the manufacturer.			
Sample Selection By:	Manufacturer	Flux Profile Run Date:	01-22-14
Number of Samples:	3	Conditioning Days:	14
Surface Exposed:	Face side exposed	Sample Color:	White
Average Thickness (in.):	0.350	Average Density (lbs/ft^2):	2.262

Test Data			
	Burn 1	Burn 2	Burn 3
Preheat Time (min):	2:00	2:00	2:00
Starting Temp. (°C):	80	78	80
Burn Length (cm):	17.2	10.4	10.2
Time to Max Burn Length (min):	10:00	10:00	10:13

Test Results			
	Burn 1	Burn 2	Burn 3
Critical Radiant Flux (W/cm2):	1.00+	1.00+	1.00+
Average Critical Radiant Flux (W/cm2):			1.00+
Standard Deviation:			N/A
Coefficient of Variation:			N/A

Observations:	None.		
Remarks:	None.		
Test Operator:	TW		

Report Prepared By: _____

Report Reviewed By: _____

Manager of Fire Testing and Field Inspections

Director of Testing, Certification, and Standards

This is a factual report of the results obtained from laboratory tests of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The HPVA does not verify the description of the materials and products when the description is provided by the client. This report is not a recommendation or a disapprobation by the HPVA of the material or product tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.