



HPVA Laboratories
42777 Trade West Drive, Sterling, VA 20166
PHONE 703-435-2900 FAX 703-435-2537

Report On
Critical Radiant Flux of Floor-Covering Systems
Using a Radiant Heat Energy Source
As Determined By
ASTM E 648 Test Method

PREPARED FOR:
Armstrong Flooring Inc.
Lancaster, PA

TEST NUMBER: FRP-1058

Striations BBT Bio-Flooring with Diamond 10 Technology Coating

Date of Issue:
12/6/2017





I. SCOPE

This report contains the reference to the test method, purpose, test procedure, preparation and conditioning of test samples, description of materials, test and post test observation data, and test results.

II. TEST METHOD

The test was conducted in accordance with ASTM Designation E648-17, "Standard Method of Test for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source." The test is also known as NFPA No. 253.

III. PURPOSE

The purpose of the test is to determine the critical radiant flux of horizontally-mounted floor covering systems exposed to a flaming ignition source in a graded radiant heat energy environment maintained in a test chamber. The specimen may be mounted over underlayment, a simulated concrete structural floor, bonded to a simulated structural floor, or otherwise mounted in a typical and representative way.

The test method provides a basis for estimating one aspect of fire exposure behavior for floor covering systems. The imposed radiant flux is designed to simulate the thermal radiation levels likely to impinge on the floors of a building whose upper surfaces are heated by flames and/or hot gases from fully developed fire in an adjacent room or compartment. The method was developed to simulate an important fire exposure component of fires which may develop in corridors or exit ways of buildings and is not intended for routine use in estimating flame spread behavior of floor covering in building areas other than corridors or exit ways.

IV. TEST PROCEDURE

The basic elements of the test chamber are: 1) an air-gas, fueled radiant heat energy panel inclined at 30° to and directed at 2) a horizontally-mounted floor covering system specimen. The radiant panel generates a radiant energy flux distribution ranging along the 100-cm length of the test specimen from a nominal maximum of 1.0 watts/cm² to a minimum of 0.1 watts/cm². The test is initiated by open flame ignition from a pilot burner. The distance burned to flame-out is converted to watts/cm² and reported as **critical radiant flux**.



**Report on Critical Radiant Flux of Floor Covering Systems Using a
 Radiant Heat Energy Source as Determined by the ASTM E 648 Flooring Radiant Panel**

Test Number: FRP-1058

Test Date: 11/09/17

Report Prepared For:	Armstrong Flooring Inc. Lancaster, PA
Material Tested:	Striations BBT Bio-Flooring with Diamond 10 Technology Coating

Sample Information:	
Detailed Product Description:	Pattern # C3601 (white). Bio-Flooring, Biobased Tile. Production Date: 09-24-17. Lot Number: E249A. Composition: Limestone-filled polyester composition. Tile Dimensions: 0.125"x12"x24". Comparable Products: Migrations BBT Bio-Flooring with Diamond 10 Technology Coating.
Sample Preparation:	The material was adhered to a 0.25" cement board backer by the manufacturer using Armstrong S-525 adhesive.
Sample Selection By:	Manufacturer
Number of Samples:	3
Surface Exposed:	Surfaces (Faces Only)
Average Thickness (in.):	0.374
Flux Profile Run Date:	11/09/17
Conditioning Days:	3
Sample Color:	White
Average Weight (lbs):	8.40

Test Data			
	Burn 1	Burn 2	Burn 3
Preheat Time (min):	5:00	5:00	5:00
Starting Temp. (°C):	183	183	185
Burn Length (cm):	7.0	5.0	4.9
Time to Max Burn Length (min):	10.28	10.47	10.06

Test Results			
	Burn 1	Burn 2	Burn 3
Critical Radiant Flux (W/cm2):	1.00	1.00	1.00
Average Critical Radiant Flux (W/cm2):		1	
Standard Deviation:		N/A	
Coefficient of Variation:		N/A	

Observations:	Blistering during the 5 minute preheat.
Remarks:	Reported weights and thicknesses include the 0.25" cement board backer.
Conclusions:	The product is classified as Class I (Critical Radiant Flux greater than 0.45 W/cm ²) by NFPA 101
Test Operator:	CK

Report Prepared By:

Report Reviewed By:

Manager of Fire Testing – Engineer

Director – HPVA Laboratories

This is a factual report of the results obtained from laboratory tests of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The HPVA does not verify the description of the materials and products when the description is provided by the client. This report is not a recommendation or a disapprobation by the HPVA of the material or product tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.