

Light Reflectivity

Bio-Flooring

Migrations® BBT™

All light reflectivity values listed are based on a percentage system, the higher the percentage (e.g. 20-24, 35-39), the higher the light reflectance of the floor. It is measured per ASTM E1349, *Standard Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry*. Research indicates reflectance can help drive daylight further into space and reduce reliance on artificial lighting, resulting in reduced electricity usage and costs. Glare from flooring is a characteristic of glossy finishes, not reflectance. Flooring in lighter colors with a matte finish have high reflectance values, but do not add to glare. Flooring with light reflectivity values great than 25% can contribute to the LEED® Interior Lighting Credit.

Value	Sku Numbers
0-9	T3546
10-14	T3531, T3540
15-19	T3528
20-24	T3529, T3542, T3544
25-29	T3534
30-34	T3509
35-39	T3547
40-44	T3533, T3535, T3537
45-49	--
50-54	T3503
55-59	--
60-64	--
65-69	--
70-74	T3543