

Light Reflectivity

LVT
Unleashed™

All light reflectivity values listed are based on a percentage system, the higher the percentage (e.g. 20-24, 35-39), the higher the light reflectance of the floor. It is measured per ASTM E1349, *Standard Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry*. Research indicates reflectance can help drive daylight further into space and reduce reliance on artificial lighting, resulting in reduced electricity usage and costs. Glare from flooring is a characteristic of glossy finishes, not reflectance. Flooring in lighter colors with a matte finish have high reflectance values, but do not add to glare. Flooring with light reflectivity values great than 25% can contribute to the LEED® Interior Lighting Credit.

Value	Sku Numbers
0-9	F0015
10-14	TP023, TP027, TP037, TP064. TP715
15-19	TP029, TP526
20-24	TP042, TP065. TP545
25-29	TP035, TP046, TP714
30-34	TP530, TP777
35-39	TP776
40-44	TP041, TP529
45-49	--
50-54	TP500
55-59	--
60-64	--
65-69	--
70-74	--