

Resistance to Staining Reagents

**LVT**

*Unleashed™*

We extensively test all our products in order to determine how our different flooring products will perform in use — and, how the flooring will react to staining reagents. Owners and specifiers know the types of substances that may potentially stain surfaces in their building. This chart is designed to provide owners and specifiers with accurate information about a wide variety of cleaners, disinfectants, foods, beverages, oils, organic solvent and other substances that may be found in buildings and affect the performance of the floor.

<b>Organic Solvents</b>	<b>Result</b>
Acetone	0
Chloroform	0
Ethyl Acetate	0
Ethyl (Denatured) Alcohol	0
Ethyl Ether	0
Ethylene Glycol (Antifreeze)	0
Formaldehyde - 10%	0
Gasoline	0
Isopropyl Alcohol	0
Kerosene	0
Methyl Ethyl Ketone (MEK)	0
Mineral Spirits	0
Toluene	0
Trichloroethylene (TCE)	0
Turpentine	0
Xylene	0
<b>Alkali (Bases)</b>	
Ammonium Hydroxide - 30%	0
Potassium Hydroxide - 15%	0
Sodium Hydroxide - 50%	3, R
<b>Acids</b>	
Acetic Acid - 28%	0
Acetic Acid - Glacial	0
Hydrochloric Acid - 38%	0
Lactic Acid - 10%	0
Nitric Acid - 15%	0
Phosphoric Acid - 85%	0
Sulfuric Acid - 40%	0
Sulfuric Acid - 10%	0

Resistance to Staining Reagents

<b>Salt Solutions</b>	
Calcium Chloride - Sat'd	0
Copper Sulfate - 10%	0
Ferric Chloride - 10%	0
Silver Nitrate - 1%	0
<b>Medical Stains &amp; Reagents</b>	
Aniline Blue - 2.5%	0
Auramine Rhodamine	3
Basic Fuchsin	3
Betadine® Skin Cleanser	2
Betadine® Solution - 10%	2
Bromocresol Green	2
Carbol Fuchsin	3
Eosin - 1%	2
Gentian Violet - 2%	3
Glutaraldehyde	0
Iodine Tincture	3
Iodine Gram Stain	3
Iodoform - 1%	0
Lugol's Solution	3
Merthiolate Tincture	0
Methylene Blue	3
Picric Acid - 1%	2
Potassium Permanganate - 0.5%	3
Tincture of Benzoin	3, R
Urea Solution	0
Wright's Blood Stain	3
<b>Disinfectants and Cleaners</b>	
Clorox®	1
Comet Bathroom Cleaner	0
Hydrogen Peroxide	0
Lysol® Liquid Disinfectant	0

Resistance to Staining Reagents

<b>Food Service</b>	
Catsup	0
Coffee - Hot Black	0
Cola Drink	0
French Dressing	0
Mustard	3
Red Food Color	3
Red Wine	0
Soy Sauce	0
Spaghetti Sauce	0
Tea - Hot Black	1
Tomato Paste	0
<b>Office</b>	
Ball Pen Ink	3
Carbon Paper Smudge	0
Fountain Pen Ink	0
Lead Pencil	0
Permanent Black Marker	3
Red Crayon	0
Red Tempura Paint	0
<b>Oils</b>	
Beef Tallow - Hot	0
Canola Oil	0
Cottonseed Oil	0
Brake Fluid	0
Dexron Transmission Fluid	0
Mineral Oil	0
Olive Oil	0
SAE #10 Oil	0
30 wt. Non-Detergent Oil	0
Used Motor Oil	0

Resistance to Staining Reagents

Miscellaneous	
Asphalt Driveway Sealer	0
Blue Chalk	0
Black Rit® Dye	1
Eye Shadow	0
Hair Color	3
Lipstick	0
Perfume	0
Red Candle Wax (Melted)	0
Red Nail Polish	3, R
Shoe Polish – Liquid Brown	0
Shoe Polish – Paste Brown	2

Samples were tested as manufactured (no additional surface treatments). All samples were exposed to reagents for 4 hours (uncovered), then cleaned with a neutral commercial cleaner and cotton cloth. A key for interpreting results is found below. It is important to note that in some cases, residual stain, residues and surface dulling may be further reduced or eliminated with different or more aggressive cleaning procedures and/or cleaning agents other than the common method used for this multi-product comparison. For further details on appropriate cleaning methods and care for specific products, please consult the care and maintenance guidelines for the specific product at [www.armstrongflooring.com](http://www.armstrongflooring.com) or contact Armstrong at 888-276-7876.

- |   |          |    |                        |
|---|----------|----|------------------------|
| 0 | No Stain | BL | Bleaching              |
| 1 | Slight   | D  | Dulling                |
| 2 | Moderate | G  | Gloss Up               |
| 3 | Severe   | S  | Softening              |
|   |          | R  | Reagent left a residue |